



Grey

Electrical Properties:

Rp-p: 10E8 ohms
Rg: 10E8 ohms per IEC 61340-4-1

Specifications:

Construction: A combination of vinyl and nitrile rubber produces an exceptional anti-fatigue product that exhibits the characteristics of better chemical resistance, improved surface durability and greater resilience than traditional vinyl foams.

Thickness: 9.5mm
Texture:* Non-directional, embossed, soil and abrasion resistant
Colour:* Grey
Weight: 0.317 g/cm²
Hardness: ASTM-D-2240-75 65 Shore "00"
Wear Resistance: Negligible-Tabor Abrader, 500 Cycles CS-17 wheels, 10,000 grams load
Heat Resistance: -20°to 140°F continuous
Flammability: Pass DOT FMVSS 302 [Horizontal Burn Test]
Pass, < 1" diameter CPSC FF 1-70 [Methenamine Tablet Test]

*Color and texture may vary between lots and mills

Grounding: This material must be properly grounded for optimum electrical performance. Ask for Technical Bulletin [PPE-5025.E](#) for mat grounding instructions.

Cleaning: For optimum electrical performance, surface must be cleaned regularly using an ESD mat cleaner. Charleswater Europe suggests using our Reztore™ Surface & Mat Cleaner Item #71021. Do not use cleaners with silicone. Silicone buildup will create an insulative film on the surface.

Disclaimer:

All statements, technical data, and recommendations contained herein are based upon tests we believe to be reliable. However, the accuracy of completeness thereof is not guaranteed. The proper and correct applications of products and data is the responsibility of the user. Statements of recommendations not contained herein shall have no force or effect unless embodied in a written agreement signed by authorized officers of Desco Industries, Inc.

Grounding Intervals for ESD Mats

Sufficient ground cords should be used to reliably meet EN 61340-5-1 Table 3 less than 1 x 10E9 ohms for Flooring. An industry recommendation has been that continuous runs of ESD matting should be grounded at three metre intervals to allow proper charge decay rates with each individual ESD mat should be grounded with ground snap located no further than 1.5 metre from either end.

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Desco Industries Inc. letter on-line at Charleswater.co.uk.

Limited Lifetime Warranty:

Charleswater warrants for one year that Statfree® matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Charleswater Limited Warranty.

Specifications and procedures subject to change without notice.

Description:

Statfree S Plus™ material is specifically designed to reduce fatigue in areas where standing is required for long periods of time. This material has been produced since 1984 and has been in the field since that time with no reported loss of electrical properties due to wear or aging. This floor mat combines ESD protection and durability.

Statfree S Plus™ meets EN 61350-5-1 Flooring limit of <1 x 10E9 ohms.

| Size (metres) | Item# |
|---------------|-----------------------|
| 0.9 x 18.3 | 80135 |
| 1.2 x 18.3 | 80136 |

| Tolerances: |
|---|
| Width +/- 6.35mm |
| Length +/- 6.35mm every 0.305m of running material. |



Statfree S Plus™ Dissipative Anti-Fatigue Vinyl/Nitrile Rubber, 9.5mm

CHARLESWATER
UNIT 17. MILLBROOK BUNSINESS PARK, SYBRON WAY
CROWBOROUGH, EAST SUSSEX TN6 3JZ UNITED KINGDOM
PHONE: 00 44 (0) 1892-665313, FAX: 00 44 (0) 1892-668838
INTERNET: www.charleswater.co.uk

Drawing Number
PME-S Plus

DATE:
February
2010