

Disclaimer:

All statements, technical data, and recommendations contained herein are based upon tests we believe to be reliable. However, the accuracy or completeness thereof is not guaranteed. The proper and correct applications of products and data is the responsibility of the user. Statements or recommendations not contained herein shall have no force or effect unless embodied in a written agreement signed by authorized officers of Desco Industries, Inc.

Limited Lifetime Warranty:

Charleswater warrants for one year that Statfree[®] matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Charleswater Limited Warranty.

Description:

Statfree EuroT2[™] material is a dual purpose rubber matting material. The two layer construction allows it to be used as a dissipative or a conductive matting product. The soft dissipative layer makes an excellent table mat, ideal for use in soldering and assembly areas. The conductive layer provides a durable slip resistant flooring surface, ideal for use in applications requiring conductive footwear. This 100% Nitrile



Electrical Properties:

See Desco Industries Inc. letter

on-line at Charleswater.co.uk.

Butadiene Rubber material has superior resistance to abrasion, chemicals and is very easy to clean and maintain. Statfree EuroT2[™] material is heat resistant and will not produce toxic fumes if exposed to extremely high temperatures. Solder and flux will not damage the surface. Statfree T2[™] is suitable for use with continuous monitors. *The green material identifies the worksurface as a Lead-Free work zone. See illustration on the reverse side.*

Statfree Euro T2™ is manufactured without any ozone depleting substances, and is in accordance with the Montreal Protocol.

Specifications:

•		
Construction: Thickness: Surface: Cleaning:	Two-layer 100% Nitrile Butadiene Rubber 1.8mm thick Abrasion resistant smooth texture For optimum electrical performance, surface must be cleaned regularly using an ESD safe mat cleaner. Charleswater suggests using Reztore [™] Surface & Mat Cleaner, item #71021. Do not use cleaners with silicone. Silicone build-up will create an insulative film on the surface.	Dissipative Side: Rp: $10^{6} - 10^{8}$ Ohms Rg: $10^{6} - 10^{8}$ Ohms Conductive Side: Rp: $10^{3} - 10^{4}$ Ohms Rg: $10^{3} - 10^{4}$ Ohms per IEC 61340-4-1
Grounding: Weight: Hardness: Temperature: Chemical Resistance:	This material must be properly grounded for optimal electrical performance. Ask for Technical Bulletin PPE-5025.E for grounding instructions. 0.2 g/cm ² 65 Shore A Continuous - 121°C, Intermittent - <30 sec @ 343°C Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic hydrocarbons, mineral oil, aldehydes, and amines	RoHS Compliance Statement None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1.



Statfree EuroT2[™] Lead-Free Dissipative Dual Layer Rubber, 1.8mm

CHARLESWATER LTD. UNIT 17. MILLBROOK BUSINESS PARK, SYBRON WAY CROWBOROUGH, EAST SUSSEX TN6 3JZ UNITED KINGDOM PHONE: 00 44 (0) 1892-665313, FAX: 00 44 (0) 1892-668838 INTERNET: www.charleswater.co.uk

Drawing Number

PME-EuroT2 Green

DATE: 2/06

Part Number Reference For Statfree EuroT2[™] Lead-Free Rubber, Dissipative, 2-layer



 7	

Roll Stock Item Numbers

SIZE	GREEN
0.6x7.3 m	80575

Hardware is not included with rolls. Grounding Intervals for ESD Mats

Sufficient ground cords should be used to reliably meet ANSI/ESD S20.20 Table 1 less than 1 x 10E9 ohms for worksurfaces. An industry recommendation has been that continuous runs of ESD matting should be grounded at three-metre intervals to allow proper charge decay rates with each individual ESD mat should be grounded with ground snap located no further than 1.5 meters from either end.

*NOTE: Sizes of mat materials are nominal dimensions.



Matting materials have a tendency to shrink slightly

when first unrolled. In applications where length is

critical, allow the material to relax for at least 4

hours before cutting to size. Always trim with a

sharp knife or razor blade.

Mat Kits



Mat Top Kit Item Numbers

SIZE	GREEN
0.6x0.9 m	80570
0.6x1.2 m	80571

Lead Free Workstation

Statfree T2[™] Lead-Free Rubber is laser engraved with "Lead-Free Workstation" to designate the area as free of lead.

TO FORM A COMPLETE MAT KIT, ADD THE FOLLOWING: Mat grounding cord Grounding hardware Wristband Coil Cord



Look for the Statfree[®] brand on Charleswater ESD matting. All Charleswater mat top kits are permanently marked for your protection and auditing purposes.